# StrataGrid™ SGU 150

StrataGrid™ uniaxial (SGU) is a polyester (PET) geogrid reinforcement for soil. These high-performance geogrids are constructed of high molecular weight polyester yarns that are knitted and coated with a proprietary coating. SGU is engineered to be mechanically and chemically durable, in both the harsh construction installation phase and in the aggressive soil environments.

| | | Unit | SGU 150 |
|---|---|---|---|
| **Mechanical properties** | | | |
| Minimum ultimate tensile strength (ASTM D6637) | MD | lbs/ft (kN/m) | 10,278 (150) |
| Minimum ultimate tensile strength (ASTM D6637) | CMD | lbs/ft (kN/m) | 2,056 (30) |
| Elongation at minimum ultimate tensile strength[(1)] (ASTM D6637) | MD | % | 8.50 |
| Creep reduction factor (at 20°C, 75 years design life) | $RF_{CR}$ | | 1.43 |
| Creep limited strength | MD | lbs/ft (kN/m) | 7,187 (105) |
| Long term design strength (LTDS) (for clay,silt and sand) | | lbs/ft (kN/m) | 6,127 (89) |
| **Physical properties** | | | |
| Roll dimensions (width x length) | | ft (m) | 6.25 x 288 (1.90 × 88)<br>12.5 x 288 (3.80 × 88)<br>12.5 x 1440 (3.80 × 440) |
| Roll area | | $yd^2$ ($m^2$) | 200 (167.20)<br>400 (334.40)<br>2000 (1,672) |
| Roll weight | | lbs (kgs) | 165.35 (75)<br>341.72 (155)<br>1,659.08 (753) |
| **Molecular properties** | | | |
| Molecular weight (GRI GG8 / ASTM D4603) | | g/mol | min. 25,000 |
| Carboxyl End Group (CEG) (GRI GG7 / ASTM D7409) | | mmol/kg | max. 30 |

**Notes**
- The above properties may change at the time of the manufacturing, storing, handling or shipping.
- The values are subject to change as per the discretion of the company.
- Partial factor – environmental effects 5<pH<8 $RF_{EN}$ 1.15
- Partial factor – installation damage (ASTM D5818) in clay, silt, and sand $RF_{ID}$ 1.02
- Varying roll widths can be provided on order – 6.23 ft / 12.47 ft / 16.40 ft / 18.70 ft
- Customised rolls with varying lengths or master rolls can be manufactured on order.
- Tested in GAI-LAP and NABL accredited laboratories.
- [(1)] Tolerance for elongation is ±2.5%

Last updated - Aug26-02
www.geogrid.com | orders@geogrid.com | +1.800.680.7750

ISO 9001, ISO 14001, & ISO 45001