

## StrataTex Geotextile Product Data Sheet

# ST-110 10 oz Nonwoven Geotextile

STRATA ST-110 is a needle-punched nonwoven geotextile made of 100% polypropylene staple fibers, which are formed into a random network for dimensional stability. STRATA ST-110 resists ultraviolet deterioration, rotting, biological degradation, naturally encountered basics and acids. Polypropylene is stable within a pH range of 2 to 13. STRATA ST-110 conforms to the physical property values listed below:

PROPERTY	TEST METHOD	UNIT	M.A.R.V. (Minimum Average Roll Value)
Weight (Typical)	ASTM D 5261	oz/yd <sup>2</sup> (g/m <sup>2</sup> )	10.0 (339)
Grab Tensile	ASTM D 4632	lbs (kN)	250 (1.11)
Grab Elongation	ASTM D 4632	%	50
Trapezoid Tear Strength	ASTM D 4533	lbs (kN)	100 (0.444)
CBR Puncture Resistance	ASTM D 6241	lbs (kN)	700 (3.11)
Permittivity*	ASTM D 4491	sec <sup>-1</sup>	1.2
Water Flow*	ASTM D 4491	gpm/sf (l/min/sm)	80 (3251)
AOS*	ASTM D 4751	US Sieve (mm)	100 (0.150)
UV Resistance	ASTM D 4355	%/hrs	70/500

\* At the time of manufacturing. Handling, storage and shipping may change these properties.

PACKAGING	
Roll Dimensions (W x L) – Feet	12.5 x 360 / 15 x 300
Square Yards Per Roll	500
Estimated Roll Weight - Lbs	320

This information is provided for reference purposes only and is not intended as a warranty or guarantee. STRATA assumes no liability in connection with the use of this information.



Strata Systems, Inc.  
380 Dahlonega Rd., Suite 200  
Cumming, GA 30040  
(770)888-6688 • (800)680-7750 • (770)888-6680 fax  
Email: [strata@geogrid.com](mailto:strata@geogrid.com) Website: [www.geogrid.com](http://www.geogrid.com)

Made in U.S.A.