## StrataTex Geotextile Product Data Sheet

## ST-160 6.0 oz Nonwoven Geotextile

STRATA ST-160 is a needle-punched nonwoven geotextile made of 100% polypropylene staple fibers, which are formed into a random network for dimensional stability. STRATA ST-160 resists ultraviolet deterioration, rotting, biological degradation, naturally encountered basics and acids. Polypropylene is stable within a ph range of 2 to 13. STRATA ST-160 conforms to the physical property values listed below:

PROPERTY	TEST METHOD	UNIT	M.A.R.V. (Minimum Average Roll Value)
Weight (Typical)	ASTM D 5261	oz/yd² (g/m²)	6.0 (203)
Grab Tensile	ASTM D 4632	lbs (kN)	160 (.711)
Grab Elongation	ASTM D 4632	%	50
Trapezoid Tear Strength	ASTM D 4533	lbs (kN)	65 (.267)
CBR Puncture Resistance	ASTM D 6241	lbs (kN)	410 (1.82)
Permittivity*	ASTM D 4491	sec <sup>-1</sup>	1.5
Water Flow*	ASTM D 4491	gpm/sf (I/min/sm)	110 (4480)
AOS*	ASTM D 4751	US Sieve (mm)	70 (.212)
UV Resistance	ASTM D 4355	%/hrs	70/500

<sup>\*</sup> At the time of manufacturing. Handling, storage and shipping may change these properties.

PACKAGING			
Roll Dimensions (W x L) – Feet	12.5 x 360 / 15 x 300		
Square Yards Per Roll	500		
Estimated Roll Weight - Lbs	195		

This information is provided for reference purposes only and is not intended as a warranty or guarantee. STRATA assumes no liability in connection with the use of this information.



Strata Systems, Inc. 380 Dahlonega Rd., Suite 200 Cumming, GA 30040

(770)888-6688 • (800)680-7750 • (770)888-6680 fax Email: strata@geogrid.com Website: www.geogrid.com